



CWP200-3K

C: Fiber Type Carbon Fiber

WR: Weaving Plain

200: Total Weight 6 oz/sq.yd / 200g/sq.m

3K: Input roving

Roll Specifications

Roll Width	Roll Weight	Roll Length
39in. / 1000 mm	44lbs / 20 kg	109 yd / 100 m
Acceptance Limits:		
±3 mm	±2%	±0.3 m

Fiber Architecture Data

Warp: 3K	12.5ends/in.	100 g/sq.m
Weft: 3K	12.5ends/in.	100g/sq.m

Technical Parameters

Area Weight	Lamination Thickness
(g/m ²)	(mm)
200 (±3%)	0.20

*Packaging: Bag with polyester film, Carton on Pallet.

** Storage: Unless otherwise specified, fiberglass products should be stored in a dry, cool and rain-proof area. The room temperature and humidity should be always maintained at 15℃~35℃ and 35%~65% respectively.

Bluston Composites Material Ltd., Co.

Office Address: Baofeng Building, New Century Avenue, Tongxiang City Zhejiang China 314500

E-mail: info@bluston.cn www.bluston.cn

Disclaimer:

The customer is solely responsible for determining the performance and fitness for a particular use of any product produced by customer utilizing a reinforcement fabric or material produced or manufactured by Bluston Composites Material Ltd.,Co. Specifications of reinforcements may change without notice.